



KLINGERSIL C-4430



Optimised combination of synthetic fibres and glass-fibre bound with NBR. Premium quality jointing with high temperature resistance in steam and water as well as excellent resistance to oils and hydrocarbons.

The Klinger group has been recognised as the market leader in gaskets and sealing for over a century. Our research and development laboratories have investigated over 250 different fibre forms in the search for asbestos free alternatives. The search has resulted in a range of high quality and high performance asbestos free materials that have been proven in service.

GENERAL PROPERTIES

- » Excellent creep resistance
- » Good steam resistance
- » Resistant to oils, fuels, hydrocarbons etc.
- » WRAS approved for use in cold potable water
- » Fire-safe
- » 3xA anti-stick finish on both sides

TESTS AND CERTIFICATIONS

- » BS 7531 Grade AX
- » BAM-tested
- » DIN-DVGW
- » DIN-DVGW W 270
- » DVGW VP 401
- » Elastomer-Guideline
- » WRAS approval
- » DNV GL
- » TA-Luft (Clean air)
- » Fire-Safe acc. to DIN EN ISO 10497
- » Fire-Safe acc. to ISO 19921

AVAILABILITY

- » Sheeting (m): 2.0 x 1.5*, 4.0 x 1.5, 2.0 x 2.0, 6.0 x 2.0
- » Thickness (mm): 0.25, 0.4, 0.5, 0.75, 1.0, 1.5, 2.0, 2.5, 3.0, 4.0

*-Denotes standard sheet size


- Also available with re-inforcements:

KLINGERSil C-4438, mild steel mesh

KLINGERSil C-4439, expanded mild steel

APPLICATION GUIDELINES

KLINGERSIL C-4430



- Caution: May be suitable but essential that you refer to Klinger for advice
- Usually Satisfactory, but suggest you refer to Klinger for advice
- Usually Satisfactory to Use Without Reference

NOTE: Chemical Compatibility must be considered in all cases.

TYPICAL SPECIFICATIONS

(Typical values based on 2mm thick material)

PROPERTIES	TEST CONDITIONS	VALUES
Compressibility (ASTM F 36 J)		9%
Recovery (ASTM F 36 J)		55%
Stress relaxation (DIN 52913)	50 MPa, 16h/ 175°C	39MPa
	50 MPa, 16h/ 300°C	35MPa
Stress relaxation (BS 7531)	40 MPa, 16h/ 300°C	31MPa
Klinger cold/hot compression 50 MPa	thickness decrease at 23°C	8%
	thickness decrease at 300°C	11%
Tightness	DIN 28090-2	0.05 mg/s.m
Specific leakrate λ	VDI 2440	$2.13e^{-05}$ mbar.l/s.m
Thickness increase after immersion in:	Oil IRM 903: 5 h/150°C	3%
	Fuel B: 5 h/23°C	5%
Average surface resistance	P_o	$4.1 \times 10^{13} \Omega$
Average specific volume resistance	P_b	$4.5 \times 10^{12} \Omega \text{ cm}$
Average dielectric strength	E_d	21.3 kV/mm
Average power factor	1kHz, ca. 2mm thick	0.03 tan δ
Average dielectric constant	1kHz, ca. 2mm thick	6.7 ϵ_r
Density		1.75 g/cm ³

HEAD OFFICE

KLINGER Ltd
Wharfedale Road
Euroway Trading Estate
Bradford BD4 6SG

Tel: 01274 688 222
Fax: 01274 688 549
www.klinger.co.uk
enquiries@klingeruk.co.uk



FM 602916 FM 10571 OHS 570166 EMS 570165

KLINGER RUNCORN

Tel: 01928 577 030
Fax: 01928 575 233

KLINGER SOUTHAMPTON

Tel: 02380 611 855
Fax: 02380 610 360

KLINGER ABERDEEN

Tel: 01224 772 962
Fax: 01224 772 953

KLINGER IMMINGHAM

Tel: 01469 575 289
Fax: 08449 676 779

KLINGER MIDDLESBROUGH

Tel: 01642 220 289
Fax: 01642 220 290

KLINGER GRANGEMOUTH

Tel: 01324 472 231
Fax: 01324 482 111