



KLINGER TOP- CHEM 2006



Modified PTFE material with excellent chemical resistance and good mechanical properties. Suitable for a wide range of applications in the chemical, pharmaceutical and food industries including strong alkaline conditions

The Klinger group has been recognised as the market leader in gaskets and sealing for over a century. Our research and development laboratories have investigated over 250 different fibre forms in the search for asbestos free alternatives. The search has resulted in a range of high quality and high performance asbestos free materials that have been proven in service

GENERAL PROPERTIES

- » Economical alternative to KLINGER Top-Chem-2000
- » Ideal for strongly alkaline environments
- » Good mechanical properties at low to medium temperatures
- » Ideal for food and pharmaceutical applications

TESTS AND CERTIFICATIONS

- » DIN DVGW
- » DNV GL
- » TA-Luft (Clean air)
- » BAM Approval for use with oxygen 130 BAR / 200°C
- » FDA Conformity


AVAILABILITY

- » Sheeting (m): 1.4 x 1.4 *
- » Thickness (mm): 1.5, 2.0, 3.0

* Can be welded to form gaskets larger than sheet size

KLINGER TOP-CHEM 2006

APPLICATION GUIDELINES



- Caution: May be suitable but essential that you refer to Klinger for advice
- Usually Satisfactory, but suggest you refer to Klinger for advice
- Usually Satisfactory to Use Without Reference

NOTE: Chemical compatibility must be considered in all cases.

TYPICAL SPECIFICATIONS

(Typical values for 2.0mm thick material)

PROPERTIES	CONDITIONS	VALUES
Compressibility ASTM F 36 J	-	4%
Recovery ASTM F 36 J	-	40%
Stress relaxation DIN 52913	30MPa, 16h/150°C	18MPa
Klinger cold/hot compression (50MPa)	Thickness decrease at 23°C	10%
	Thickness decrease at 250°C	40%
Gas leakage according to DIN 28090-2	-	0.1 mg/s.m
Thickness increase after fluid	HNO ₃ 100%:18h/23°C	2%
Immersion ASTM F 146	NaOH 33%, 72h/110°C	12%
Density	-	2.9g/cm ³

HEAD OFFICE

KLINGER Ltd
Wharfedale Road
Euroway Trading Estate
Bradford BD4 6SG

Tel: 01274 688 222
Fax: 01274 688 549
www.klinger.co.uk
enquiries@klingeruk.co.uk

KLINGER RUNCORN

Tel: 01928 577 030
Fax: 01928 575 233

KLINGER SOUTHAMPTON

Tel: 02380 611 855
Fax: 02380 610 360

KLINGER ABERDEEN

Tel: 01224 772 962
Fax: 01224 772 953

KLINGER IMMINGHAM

Tel: 01469 575 289
Fax: 08449 676 779

KLINGER MIDDLESBROUGH

Tel: 01642 220 289
Fax: 01642 220 290

KLINGER GRANGEMOUTH

Tel: 01324 472 231
Fax: 01324 482 111



FM 602916

FM 10571

OHS 570166

EMS 570165