





**KLINGER KLINGER UNITS** COMPONENT **THERMICA SOFTCHEM** 12 50-60 Compressibility 13-17 Recovery <55 Stress Relaxation (DIN 52913, 50MPa, MPa 28 16h, 300°C) Density g/cm<sup>3</sup> 1.7 0.9 Dielectric Strength kV/mm 15 °С -200 to 350 Temperature Range -200 to 260

Simple to install, the Safeguard limits further corrosion, giving asset managers and engineers essential quality assurance and cost savings.

- » Klinger Safeguard uses Thermica outer facing which is a CNAF fibre; using mica and NBR binder offers high flexibility, high temperature resistance and excellent compatibility across a broad range of chemicals. The ePTFE inner corrosioncompensating zone helps to fill voids at the gasket bore and reduce the likelihood of further corrosion.
- » Regular corrosion inspection activities can be completed with the knowledge that joints can be remade even if corroded flanges are evident. This is facilitated with the Klinger Safeguard without the need for expensive and disruptive flange replacement machining.
- » The risk of leaks is reduced, minimising the environmental impact of any installation.
- » Halts in production are also reduced. avoiding major loss of revenue.

### **PROPERTIES**

- » Continuous service up to 260°C
- Suitable for RTJ, RF and mismatched RF to RTJ flanges
- Suitable for pressure ratings from Class 150 to 2500
- Compressed fibre facings of mica & synthetic fibres bound with NBR on a high strength metallic core
- Excellent chemical resistance
- 3xA anti-stick finish

# TESTS AND CERTIFICATIONS FOR KLINGER **THERMICA**

- Fire-safe to DIN EN ISO 10497 / API 607
- Fire-safe to API 6FB
- BS 7531 Grade AX

## **HEAD OFFICE**

KLINGER Ltd Wharfedale Road Euroway Trading Estate Bradford BD4 6SG

Tel: 01274 688 222 Fax: 01274 688 549 www.klinger.co.uk enquiries@klingeruk.co.uk



9100 Series

FM 602916

ISO 9001 Quality

FM 10571

OHSAS 18001 Health & Safety ISO 14001 Management

OHS 570166 EMS 570165

### KLINGER RUNCORN

Tel: 01928 577 030 Fax: 01928 575 233

KLINGER SOUTHAMPTON Tel: 02380 611 855

Fax: 02380 610 360 KLINGER ABERDEEN

Tel: 01224 772 962 Fax: 01224 772 953

### KLINGER IMMINGHAM

Tel: 01469 575 289 Fax: 08449 676 779

KLINGER MIDDLESBROUGH

Tel: 01642 220 289 Fax: 01642 220 290

KLINGER GRANGEMOUTH

Tel: 01324 472 231 Fax: 01324 482 111